

AD-A071 738

CORNELL UNIV ITHACA N Y SCHOOL OF ELECTRICAL ENGINEERING F/G 20/12
GROWTH AND CHARACTERIZATION OF HIGH PURITY LATTICE MATCHED GAIN--ETC(U)
JUN 79 J D OLIVER, L F EASTMAN

N00014-75-C-0739

NL


UNCLASSIFIED

1 OF 1
AD
A071738



END
DATE
FILMED

8-79
DDC



LEVEL

Accepted for presentation at the
Electronic Materials Conf. 6/79

N00014-75-C-0739 Date: 22 June 1979

ADA 071 738

6

GROWTH AND CHARACTERIZATION OF HIGH PURITY LATTICE MATCHED GaInAs on InP

10

James D. / Oliver, Jr. and Lester F. / Eastman
Cornell University
School of Electrical Engineering, Phillips Hall
Ithaca, N.Y. 14853

12
B.S.

DDC


JUL 26 1979

11 22 JUN 79

ABSTRACT

> The high mobility of GaInAs allows its potential use as a field effect transistor active layer in either microwave, or high speed logic applications, provided that doping levels can be adequately controlled. At the present, doping levels of less than 10^{16} cm^{-3} are difficult to achieve.¹ Previous studies have identified silicon as the major residual donor in InP² and GaAs. Here we report on the highest purity GaInAs produced, by carefully controlling the incorporation of silicon.¹⁵ N00014-75-C-0739

It is shown that the thermochemistry of the process



12 2 P.

is applicable and is supported by the experimental results. Using the purging process of long time baking at the growth temperature, we have achieved room temperature Hall results:

$$n_{\text{RT}} = 5 \rightarrow 10 \times 10^{14} \text{ cm}^{-3}, \mu_{\text{RT}} = 11,500 \rightarrow 13,500 \text{ cm}^2/\text{V} \cdot \text{sec}$$

and liquid nitrogen Hall mobilities as high as $\mu_{77} = 57,000 \text{ cm}^2/\text{V} \cdot \text{sec}$ with little freeze out. The nitrogen mobility (μ_{77}) increases with baking time and has not yet reached its equilibrium value.

DDC FILE COPY

79 07 16 156 098 850

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

This high mobility supports the predictions that alloy scattering may not have as great an effect as was originally thought.¹

Variable temperature Hall analysis is being conducted in an attempt to estimate the amount of scattering by various mechanisms. This will enable us to estimate the total ionized impurity density, as well as the extent of alloy and space-charge scattering in our high purity material.

X-ray techniques were used to measure the mismatch and structural quality of the high purity layers. Diffraction techniques showed that the mismatch was less than $.06\% \frac{\Delta a}{a}$ and that the lattice constant was uniform over the entire layer. An electron microprobe was used to measure the material composition. No evidence of inclusions or inhomogenities was found.

References:

1. Littlejohn, Sadler, Glission, Hauser, 7th Intl. Symp. on GaAs, 1978, to be published.
2. Wrick, Ip, Eastman, J. Electronic Materials, Vol. 7, No. 2, 1978.

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DDC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or special
A	